

# Technical data sheet



## ENZINRON (PP)

	METHOD	UNIT	VALUE
<b>Mechanical Properties</b>			
Specific gravity	ASTM D792	g/cm3	0.9
Tensile yield strength	ASTM D638	Mpa	29
Breaking elongation	ASTM D638	%	300
Bending strength	ASTM 790	Mpa	35
Flexural modulus	ASTM 790	Mpa	1030
Shore hardness	ASTM D2240	D	83
Impact strength	ASTM D256	J/M	35
<b>Thermal Properties</b>			
Melting point	DSC	°C	170
Heat distortion temperature	ASTM D648	°C	83
Operating temperature	-	°C	95
Maximum operating temperature	-	°C	120
Coefficient of linear thermal	ASTM D696	10-5- 1/K	15
<b>Electrical Properties</b>			
Dielectric strength	ASTM D150	KV-mm	40
Volume resistivity	ASTM D257	Ω.cm	10 <sup>14</sup>
Surface resistivity	ASTM D257	Ω	10 <sup>13</sup>
Dielectric constant	ASTM D149	-	2.3
<b>Chemical Properties</b>			
Water absorption	23°C 60%RH	%	0.05
Acid resistance	23°C 60%RH		+
Alkali resistance			+
Acid and alkali resistance			+
Resistance to sodium chlorate			+
Resistance to aromatic compounds			-
Resistance to ketone	23°C 60%RH		+
Resistance to hot water	23°C 60%RH		+
<b>Others</b>			
Flammability	UL 94	HB	
Viscosity	-		+
Non toxic	EEC 90/128 FDA		+
Coefficient of friction	DIN 53375		0.3
Anti-ultraviolet	-		0

**Remarks:**

- 1.“+”: positive “-”: negative “0”: depends.
2. All the parameters above are based on raw material but not finished products.